

## TI 254K

Technical Information Surface Protection Linings  
Issue 13.11.2020

# GENAKOR 022

Hard rubber lining for steel components protection with approvals for the transportation of hazardous materials according to TRT 010 and TRT 008

## Base

Polyisoprene rubber (IR)

## Material Group

Workshop rubber linings

## Description

Graphite-filled hard rubber lining based on polyisoprene rubber (IR) that is vulcanized in the autoclave. Depending on the requirements, the layer thickness of the rubber sheet can be 3 - 6 mm.

## Use

GENAKOR 022 is recommended as a protective lining for structural components made of steel that are subjected to chemical exposure.

Its primary spectrum of application includes the lining of flue gas scrubbers in garbage incineration plants, as well as storage tanks and reaction vessels that are operated at high temperature ranges.

## Properties

GENAKOR 022 is characterised by its excellent chemical resistance to alkaline and acidic media, with the exception of oxidising media. GENAKOR 022 cannot be spark tested.

## Physical Data

Property [unit], Test method	Value
Density [g/cm <sup>3</sup> ], DIN EN ISO 1183-1, ASTM D 792	1.4 ± 0.02
Tensile strength [MPa], DIN 53504 *	≥ 20
Adhesive strength [N/mm <sup>2</sup> ], DIN EN ISO 4624	≥ 6
max. surface pressure [MPa]	10
Temperature resistance [°C]	125
Elongation at tear [%], DIN EN ISO 527, ASTM C 307	> 2
Shore D hardness, DIN 53505, ASTM D 2240	78 ± 5
Data are mean values	

\*) The values were determined at 4 mm thick rubber samples.

## Chemical Resistance

Information on chemical resistance is available on request.

**Container change!**  
**Vulkodurit-Adhesive LS3A (22) 5040253014**  
**Seam-Solution 2104/N1 (18) 5040703040**

## Substrate

### Steel

Refer to DIN EN14879-1 as well as to STEULER-KCH-Formsheet 020 and 030.

The steel surface is to be blasted to a metallic bright finish. A preparation degree of SA 2 ½ as specified in DIN EN ISO 12944-4 and a roughness grade “medium (G)” as specified in DIN EN ISO 8503-1 must be achieved; minimum surface roughness  $R_z = 50 \mu\text{m}$ . After blasting, a new formation of rust is to be avoided by appropriate procedures, e. g. immediate application of a primer.

Stainless steel must be abrasive blasted with non-ferritic abrasives.

Grey cast iron must be tempered in the autoclave prior to blast cleaning, in order to expel any inclusions of moisture.

The substrate temperature should be in the range of approx. 10 - 30 °C, dew point distance min. 5 K.

Relative humidity:  $\leq 75 \%$

During application, the substrate must be kept absolutely dry. No moisture (condensate, mist, etc.) must get onto the material.

## Packaging / Shelf life

All components must be stored and transported dry. Unless otherwise specified, the minimum shelf life applies to a storage temperature of 20 °C. Higher temperatures reduce, lower temperatures increase the minimum shelf life. The use of refrigerated containers should be considered on a project-by-project basis, especially when components are to be stored at temperatures below 20 °C in order to extend their shelf life. Keep the containers tightly closed (especially after material removal).

Component	Item number	Package	Content	Shelf life
Genakor-022-Sheet	6071603200–600	Roll		6 Months 12 Months < 15 °C
Primer 1	5040271039	Hobbock	23 kg	12 Months
Primer 2	5040274001	Hobbock	25 kg	12 Months
Vulkodurit-Adhesive LS3A	5040253020	Hobbock	16 kg	6 Months
Vulkodurit-adhesive LS3A for rubber lining of pipes	5040269020	Hobbock	16 kg	6 Months
Seam-Solution 2104/N1	5040703021	Hobbock	15 kg	12 Months
KCH-Diluent 5	5040021041	Canister	8 kg	24 Months
Genakor-022-R-Sheet	6071604200–600	Roll		3 months < 15°C

For handling, transport and storage observe the relevant safety data sheets.

## Application

The GENAKOR 022 rubber lining system is composed of the one-component Primer 1, the one-component Primer 2, the one-component Vulkodurit adhesive LS3A and the Genakor-022-Rubber-Sheet.

Spread Primer 1 and Primer 2 on the substrate. Then apply two coats of the Vulkodurit -adhesive LS3A.

The rubber sheets are coated with Vulkodurit-Adhesive LS3A and bonded to the substrate in accordance with the specifications contained in DIN EN 14879-4. A permanent and firm bond is achieved by pressing the rubber sheet and the subsequent vulcanization process.

### Consumption

Primer 1	approx. 0.15 kg/m <sup>2</sup>
Primer 2	approx. 0.20 kg/m <sup>2</sup>
Vulkodurit-Adhesive LS3A	approx. 0.25 kg/m <sup>2</sup> per coat

## Safety and Disposal

- sufficient aeration and de-aeration (especially in tanks and pits)
- no smoking/no fire
- refer to the safety data sheets.
- observe hazard warnings and safety instructions on labels.
- wear required personal protective equipment (avoid skin contact with materials).
- clean and protect hands with skin protective soap and skin protection cream (no solvents).
- wear a dust mask when grinding (e.g. for repairs).
- operating instructions as per § 14 of GefahrstoffV (Toxic Substances Act) and TRGS 507 (Technical regulations for Hazardous Substances - Germany).
- accident prevention regulations by the Liability Insurance Association for the Chemical Industries (Germany).

Avoid direct contact of the materials with the flame, especially during welding work (welding beads) on site.

Preferably consume residual quantities. Do not pour into a spout or dustbin! Collect separately for disposal in durable, lockable and labelled containers.

## Cleaning of Equipment

The tools are cleaned with KCH Diluent 5 or STEULER UNIVERSAL CLEANER. Cleaning must be carried out prior to hardening of the material.

All information contained in this Technical Information is based on the present state of our knowledge and practical experience. All data are approximate values for guidance only. A legally binding warranty of certain characteristics or the suitability for a certain purpose of use cannot be derived from this.

The information given in this Technical Information is our intellectual property. The Technical Information may neither be copied nor used by unauthorized parties, nor professionally distributed or otherwise made accessible to third parties without our prior consent.

This issue replaces all previous versions.